

MORTAR PLASTICISER

Thompson's Mortar Plasticiser is a surfactant based liquid admixture for modifying cement mortar used in brick laying and pointing mortar, back coats, renderings and blockwork. It is designed to improve plasticity without the addition of lime and increases resistance to freeze thaw cycles in the set mortar.



THOMPSON'S MORTAR PLASTICISER:

- Reduces the amount of water required
- Increases resistance to freeze thaw in the set mortar
- Minimises cracking and crazing
- Conforms to BS EN 934

TECHNICAL DATA

Form	Liquid
Storage Life	12 Months stored between 5°C and 25°C in original containers

Specification writers: These values are not intended for use in preparing specifications. Please contact your local Thompson's Sales Representative prior to writing specifications on this product.

APPLICATION

Thompson's Mortar Plasticiser may be added directly to the mixture or mixed with the gauging water. The gauging water should be reduced accordingly to meet the required consistency.

ADDITION RATE

Add Thompson's Mortar Plasticiser to a rate: 150ml-500ml per 50kg of cement, depending upon degree of plasticising required, or 2.5 litre per 200 litre drum of water. (The coarser the sand the greater addition rate required). Thompson's Mortar Plasticiser can be used with all types of Portland cement, however, if the cement is already plasticised a trial mix is recommended.

PACKAGING

Sizes: 5L, 25L

LIMITATIONS

Do not use in structural concrete. Thompson's Mortar Plasticiser is not compatible with calcium chloride admixtures.

HEALTH AND SAFETY

Thompson's Mortar Plasticiser is essentially non hazardous in normal use, however refer to full Health and Safety data sheet available on request.

TECHNICAL SERVICE

For further technical information, advice on suitability for specific applications, or detailed Health and Safety information, contact Thompson's Technical Service.

IMPORTANT NOTE The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that Thompson's products are safe, effective and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Thompson's sole warranty is that the product will meet the Thompson's sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

Thompson's specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability.

Thompson's disclaims liability for any incidental or consequential damages.